



# TECHNICAL DATA SHEET

TECHNICAL DATA SHEET  
DC740 RUST-GARD RED OXIDE PRIMER  
200R65  
PAGE 1 OF 2

**PRODUCT:** A water-base, high-solids primer for ferrous metal. TriCom's RUST-GARD Primer is a single-component, modified alkyd coating formulated for maximum rust prevention.

**DESCRIPTION:** A highly rust-resistant primer designed for ferrous and non-ferrous metal. TriCom's RUST-GARD is a high solids product that offers superior adhesion and abrasion resistance. RUST-GARD is fast dry, easy to use and compatible with virtually all industrial topcoats. Formulated with the environment in mind, RUST-GARD is a low "VOC" product that uses water to clean-up. It is also lead and chromate free.

**PROPERTIES:**

COLOR.....	Red Oxide
SOLIDS(Weight).....	58 - 60%
MATERIAL "VOC".....	200 G/L
THEORETICAL COVERAGE.....	516 mil sq.ft/gal
DRY FILM THICKNESS.....	2.0 to 2.5 mils p/coat

**DRYING TIME-AT 75 DEGREES F:**

TO HANDLE.....	30 Minutes
TO RECOAT.....	2 Hours
VEHICLE TYPE.....	Modified Alkyd
WEIGHT/GAL.....	10.8 - 11.1 lbs/gal
<b>SALT SPRAY.....</b>	<b>300+ Hours ASTM STD. B117</b>
<b>TEMPERATURE RESISTANCE.....</b>	<b>Up to 250 degrees F</b>

**ADVANTAGES:**

- (1). Low Volatile Organic Compound Content
- (2). Excellent Corrosion Resistance
- (3). Excellent Foundation
- (4). Extremely Abrasion Resistant
- (5). Water Reducible
- (6). Water Clean-Up
- (7). Low V.O.C.

**USES:**

- (1). Steel
- (2). Machinery
- (3). Tanks
- (4). Bridges



# TECHNICAL DATA SHEET

(5). Equipment

TECHNICAL DATA SHEET  
RUST-GARD RED OXIDE PRIMER 200R65  
PAGE 2 OF 2

## **APPLICATION & REDUCTION:**

TriCom's RUST-GARD Primer can be applied by brush, roll or spray. For brushing and rolling, use as is or thin with Water.

For spraying, thin up to 15% or as needed with Water.

Reduce with Cold Weather Reducer for cold/humid conditions.

## **SURFACE PREPARATION:**

Surface must be clean, dry and free of all contamination before application.

## **STEEL:**

Surface must be clean and free of all oil, grease and foreign material. Badly rusted or pitted steel should be cleaned by commercial sandblasting and primed the same day.

## **PRECAUTIONS:**

KEEP OUT OF THE REACH OF CHILDREN.

Do not take internally.

Avoid breathing vapor or mist.

Do not use in tank or pit without proper protection.

Read Material Safety Data Sheet before use of this product.

Keep From Freezing.