



# TECHNICAL DATA SHEET

TECHNICAL DATA SHEET  
MIL-DTL-15090D  
EQUIPMENT ENAMEL  
PAGE 1 OF 2

**PRODUCT:** A general purpose enamel with good durability for use on steel furniture, machinery and equipment aboard ships or at naval installations. Available in two classes and three types as listed below.

**PROPERTIES:**

COLORS.....Gray  
GRIND..... Not Under 6  
SPECULAR GLOSS..... 20 - 65  
VISCOSITY..... 67 - 100 KU  
(52-68 SECONDS ZAHN #3 CUP)

**DRYING TIME-AT 75 DEGREES F:**

SET-TO-TOUCH: 1 HR,  
DRY HARD: 8 HOURS

**USES:**

- (1). Steel
- (2). Machinery
- (3). Furniture
- (4). Switchboards
- (5). Equipment



# TECHNICAL DATA SHEET

TECHNICAL DATA SHEET  
MIL-DTL-15090C  
PAGE 2 OF 2

## APPLICATION & REDUCTION:

MIL-DTL-15090D Equipment Enamel Type I can be applied by brush or spray with Types II and III designed primarily for spray application. Types I and II should be thinned 15 - 20% with Xylene. Type III should be thinned with Griggs T0123 Griggs Baking Enamel Reducer at 40%-45% by volume for spray application. Spray one tack coat followed by one full wet coat. For Type III, allow part to air dry for 30-45 minutes at room temperature. Pre-heat oven to 250-300 Degrees Fahrenheit, place part in oven and bake for 30-45 minutes.

## SURFACE PREPARATION:

Surface must be clean, dry and free of all contamination before application of primer.

## STEEL:

Surface must be clean and free of all oil, grease and foreign material. Badly rusted or pitted steel should be cleaned by commercial sandblasting and primed the same day.

## PRECAUTIONS:

Contents are FLAMMABLE.

Keep away from heat and open flame.

KEEP OUT OF THE REACH OF CHILDREN.

Do not take internally.

Avoid breathing vapor or mist.

Do not use in tank or pit without proper protection.

Read Material Safety Data Sheet before use of this product.