



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET
P-900-66 EPOXY SURFACER
(WS24780)
PAGE 1 OF 1

PRODUCT: A pure epoxy resin base surfacer with good adhesion to wood, metal, and fiberglass surfaces. It has excellent filling and sanding properties.

PROPERTIES:

SOLIDS (Weight)..... 35% Minimum
SOLIDS (Volume)..... 27% Minimum
COLORS..... Gray

DRYING TIME:

DRY HARD..... Within 2-4 Hours
SHELF LIFE.....1 Year
THINNER..... T-262A-66 or MIL-T-81772B TY.II

MIXING/APPLICATION INSTRUCTIONS:

P-900-66 is mixed one to one (1:1) by volume with C-916-66 converter or four to one (4:1) by volume with P-900-66 epoxy catalyst. After mixing the two components, allow to stand (induct) for one (1) hour before use. Thinning and clean up of equipment may be done with TriCom's T-262A-66 epoxy thinner or MIL-T-81772B Ty. II Epoxy thinner.

PRECAUTIONS:

KEEP OUT OF REACH OF CHILDREN.
USE WITH ADEQUATE VENTILATION.
AVOID CONTACT WITH SKIN AND EYES.
READ MATERIAL SAFETY DATA SHEET BEFORE USING.
CONTENTS ARE FLAMMABLE.