



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET
WATERBASE ACRYLIC
Pool Deck Coating
PAGE 1 OF 2

PRODUCT: A waterborne modified acrylic coating that is formulated specifically for use on properly prepared concrete and masonry surfaces.

DESCRIPTION: A specially formulated modified acrylic based coating for exterior and interior concrete and masonry surfaces. It has excellent resistance to stains from spills of mineral oils, vegetable oils, greases, water, alkali and acids.

PROPERTIES: COLORS.....Full Range
SOLIDS(Weight).....55 - 59%*
THEORETICAL COVERAGE.....250 - 400 sq.ft/gal DRY
FILM THICKNESS.....1 mil @ 350 sq.ft./gal

DRYING TIME-AT 75 DEGREES F:

TO TOUCH.....2 - 4 Hours
TO RECOAT.....8 Hours
VEHICLE TYPE.....Acrylic Polymer
WEIGHT/GAL.....10.4 - 11.2 Lbs*
* Values may vary with color.

ADVANTAGES: (1). Waterbase
(2). Low V.O.C. Content
(3). Seals Surface
(4). Moisture Resistant
(5). UV Resistant

USES: (1). Masonry
(2). Brick
(3). Block
(4). Kool Decks
(5). Stucco



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET
WATERBASE ACRYLIC
Pool Deck Coating
PAGE 1 OF 2

APPLICATION & REDUCTION:

TriCom's Waterbase Acrylic Pool Deck Coating can be thinned with water as needed for application purposes. Thin up to 1/2 pint of water per gallon of coating. First coat should be thinned 25% by volume with water for proper penetration on bare concrete or masonry surfaces. Apply second coat at packaged consistency.

SURFACE PREPARATION:

Surface to be coated must be free from all dirt, grease and contamination before application. Chalky surfaces must be sealed with Chalk-Bond before painting. Loose or peeling paint must be scraped and made sound before applying over previously painted surfaces.

PRECAUTIONS:

Keep from Freezing.

Do not use below 55 Degrees F.

KEEP OUT OF THE REACH OF CHILDREN.

Do not take internally.

Avoid breathing vapor or mist.

Do not use in tank or pit without proper protection.

Read Material Safety Data Sheet before use of this product.