



# TECHNICAL DATA SHEET

ZINC RICH PRIMER  
ASAE-AMS-38336  
PAGE 1 OF 2

**PRODUCT:** A lead-free, high-solids zinc-dust primer for steel surfaces. This primer is compatible with aliphatic polyurethane and enamel topcoats such as MIL-C-83286B and MIL-C-85285C.

**DESCRIPTION:** An inorganic type paint which produces a film containing high metallic zinc in contact with the steel. Like galvanizing, this zinc is electrically conductive, thereby preventing corrosion electro-chemically. It is also suitable as a finish coat on all ferrous and galvanized surfaces.

**PROPERTIES:** COLOR..... Gray  
SOLIDS(Weight)..... 79 %  
THEORETICAL COVERAGE..... 1000-1015 mil sq.ft/gal  
DRY FILM THICKNESS..... 2.0 to 3.0 mils p/coat  
**DRYING TIME-AT 75 DEGREES F:**  
TO HANDLE..... 1 Hour  
TO RECOAT..... 18 Hours  
WEIGHT/GAL..... 23 Lbs

**ADVANTAGES:** (1). Meets Steel Structures Painting Council (S.S.P.C.) requirements.  
(2). High Zinc Content.  
(3). Provides Galvanic Protection to Steel.  
(4). Excellent Corrosion Resistance  
(5). Excellent Foundation  
(6). Extremely Abrasion Resistant

**USES:** (1). Steel  
(2). Machinery  
(3). Tanks  
(4). Railings  
(5). Equipment  
(6). Towers



# TECHNICAL DATA SHEET

ZINC RICH PRIMER  
ASAE-AMS-38336  
PAGE 2 OF 2

## APPLICATION & REDUCTION:

ASAE-AMS-38336 Zinc Rich Primer can be applied by brush, roll or spray. For spraying, thin up to 15% or as needed.

## SURFACE PREPARATION:

Surface must be clean, dry and free of all contamination before application of primer.

## STEEL:

Surface must be clean and free of all oil, grease and foreign material. Badly rusted or pitted steel should be cleaned by commercial sandblasting and primed the same day.

## MIXING INSTRUCTIONS:

Combine 1 gallon of vehicle to pre-measured gallon of zinc dust by slowly mixing the zinc dust portion into the vehicle while under constant agitation. Mix thoroughly to disperse any lumps of zinc dust that may form while combining. After complete mixing, strain the admixed material before application.

## PRECAUTIONS:

Contents are FLAMMABLE.

Keep away from heat and open flame.

KEEP OUT OF THE REACH OF CHILDREN.

CAUTION: Combined material may form gas and buldge container. Do not take internally.

Avoid breathing vapor or mist.

Do not use in tank or pit without proper protection.

Read Material Safety Data Sheet before use of this product.