



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET
TC-710 Waterborne
Alkyd Primer
Page 1 of 2

PRODUCT: A water-base, corrosion/rust-resistant primer for ferrous metal. TC-710 Water-Reducible Enamels are single-component, waterborne alkyd coatings formulated for maximum rust prevention. They are extremely low VOC.

DESCRIPTION: A high quality, corrosion, rust-resistant, industrial grade water reducible primer for steel. These primers have an extremely low VOC content. TC-710 Waterborne Enamels have excellent exterior durability and dry to a hard / durable finish.

PROPERTIES: COLORS..... Red Oxide / Gray
SOLIDS (Weight)..... 50 - 60%
THEORETICAL COVERAGE..... 500 mil sq.ft/gal
DRY FILM THICKNESS..... 2.0 to 2.5 mils p/coat
VOC CONTENT..... Less than 10 G/L
DRYING TIME-AT 75 DEGREES F:
TO HANDLE..... 30 - 45 Minutes
TO RECOAT..... 60 Minutes
VEHICLE TYPE..... Waterborne Alkyd
WEIGHT/GAL..... 9.5-10 lbs/gal
TEMPERATURE RESISTANCE..... Up to 250 degrees F

ADVANTAGES: (1). Low Volatile Organic Compound Content
(2). Excellent Exterior Durability
(3). Hard / Durable Finish
(4). Abrasion Resistant
(5). Water Reducible
(6). Water Clean-Up
(7). Industrial Finish

USES: (1). Steel
(2). Machinery
(3). Parts
(4). Tools
(5). Equipment



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET
TC-710 Waterborne
Alkyd Primer
Page 2 of 2

APPLICATION & REDUCTION:

TC-710 Waterborne Primers can be reduced with water up to 10-15% by volume for spraying applications. For high build applications, however, they can be used as packaged. Thin as needed with water for smooth flow and leveling of the paint film.

SURFACE PREPARATION:

Surface must be properly prepared, clean, dry and free of all contamination before application of enamel topcoat.

STEEL:

Surface must be properly prepared clean and free of all oil, grease and foreign material. Badly rusted or pitted steel should be cleaned by commercial sandblasting and primed the same day.

PRECAUTIONS:

KEEP OUT OF THE REACH OF CHILDREN.
Do not take internally.
Avoid breathing vapor or mist.
Do not use in tank or pit without proper protection.
Read Material Safety Data Sheet before use of this product.
Keep From Freezing.